

## Solvent-free Floor Oil based on vegetable oils and waxes

### Characteristics

Hard-wearing, resistant to wine, beer, cola, coffee, tea, fruit juices, milk and water according to DIN 68861 1A. Resistant to saliva and sweat according to DIN 53160. Meets all the demands of children's toys according to EN 71. Floorservice Hardwax-Oil Pro deepens the natural structure and colour of the treated surface.

### Applications

All kind of parquet and wooden floors, as sealer or final treatment.

**Contains:** castor oil, natural resin-ester, safflower oil, kaolin, bentonite, microwax, silicic acids, zinc carbonate, cobalt, zirconium, zinc and manganese octoate as drying components.

### Technical data

**Working temperature:** not below 16°C.

**Hardening time:** 10 days.

**Drying time:** 8-12 hours, depending on temperature and ventilation. After a drying time of 3 days the floor can be used with caution.

**Usage:** 1 litre = about 16 - 20 m<sup>2</sup> in two layers or 33 - 40 m<sup>2</sup> in one layer.

**Cleaning tools:** with Floorservice Parquet Cleaner.

**Storage:** cool and dry. In case of an already opened packaging skin forming could appear. The skin has to be removed before using the product.

**Warning:** put clothes drenched with Hardwax-oil Pro in water (danger of spontaneous combustion!). Afterwards they can be disposed off with normal garbage.

**Cleaning:** Floorservice Parquet Cleaner.

**Maintenance:** Floorservice Maintenance Oil.

EU-limit for this product (cat. A/e): 400 g/l (2010). This product contains max. 20 g/l VOC.

**Packing:** 250 ml, 1 litre and 5 litre.

### Instructions for use

Stir well.

Hardwax-Oil Pro is ready to use. The surface must be well sanded (up to grain 120), dry (humidity of the wood max. 14%) and free of dust and grease. Apply the Hardwax-Oil Pro thinly and evenly using the special floorbrush, a mop or a spatula. Within 30 to max. 60 minutes rub the oil in with a buffing machine using a thick white pad and remove excess oil with a felt pad. In case of a very absorbent surface apply a second layer accordingly.

*Above product information and recommendations are given in good faith and based on practical tests following long term research and development. We cannot assume responsibility for any work as the ultimate results depend on factors beyond our direct control. In cases of doubt always test the product in advance.*

01.10.2009

